



Europäisches
Patentamt
European Patent
Office
Office européen
des brevets

[Claims of EP0230977](#)
[Print](#)
[Copy](#)
[Contact Us](#)
[Close](#)

Result Page

Notice: This translation is produced by an automated process; it is intended only to make the technical content of the original document sufficiently clear in the target language. This service is not a replacement for professional translation services. The esp@cenet® Terms and Conditions of use are also applicable to the use of the translation tool and the results derived therefrom.

1. Defoamer on base of oil in water emulsions, with those the oil phase of the emulsions

- (A) a C12 to C26-Alkohol, distillation residues, those with the production of alcohols with a higher carbon number by Oxosynthese or after the Ziegler method available and if necessary still the alkoxylated are and/or
- (B) a fatty acid ester from C12 to C22-Carbonsäuren with an in to trivalent c1 to C18-Alkohol and if necessary
- (C) an hydrocarbon with a boiling point above 200 DEG C or fatty acids with 12 to 22 carbon atoms

contains, to 5 to 50 Gew.% at the structure of the emulsion involved is and a middle particle size of < , characterised in that the oil in water emulsions has 25 µm superficially hydrophobierte, finely divided, practical water-insoluble, inert solids contained.

2. Entschäumer according to claim 1, characterised in that the non-aqueous components of the oil in water emulsion from 50 to 99.9 Gew. - % of the oil phase and 50 to 0, 1 Gew. - < % from superficially hydrophobierten, finely divided, practically water-insoluble, inert solids of a particle diameter of; 20 µm exist.

3. Defoamers after the claims 1 and 2, characterised in that as superficially hydrophobierte, finely divided, practically water-insoluble, inert solids kaolin, layer silicates, chalk, calcium sulfate, barium sulphate, talcum powder, titania, alumina, silicon dioxide, Satinweiss, micro-crystalline cellulose, urea and Melamin formaldehydepigments and/or crosslinked starch or their mixtures used become.

4. Method to the production of the defoamers after the claims 1 to 3, characterised in that one the superficially hydrophobierten, finely divided, inert solids first with the compounds (A) and/or (B) and (C) homogenized and the mixture subsequent in waters emulsifies if necessary.

5. Method to the production of the defoamers after the claims 1 to 3, characterised in that one the superficially hydrophobierten, finely divided inert solids into an emulsion of the compounds (A) and/or (B) and (C) in waters in-emulsifies if necessary.

6. Use of the 5 oil in water emulsions as defoamers with the production of paper, prepared in accordance with the claims 4 and.

⌘ [top](#)